

Advanced Materials

RenCast® 6427 A / RenCast® 5427 B

FOR THE PRODUCTION OF FLEXIBLE CASTINGS AND IN APPLICATIONS REQUIRING HIGH LEVELS OF TOUGHNESS AND DURABILITY

KEY PROPERTIES

- Flexible
- High tear strength and elongation
- Withstand moisture well, thus also suitable for thin layers
- High abrasion resistance

APPLICATIONS

- Ceramic Industry
- Concrete moulds
- Abrasion and impact-resistant parts
- Rubberlike prototype parts
- Impact protection
- Conveyor rollers
- Machinery Parts
- Assembly jigs
- Vibration absorption

PRODUCT DATA

Property	Unit	RenCast® 6427 A	RenCast® 5427 B
Appearance Colour	visual	Liquid clear	Liquid amber
Viscosity at 25 °C	mPas	600 - 900	2200 - 3200
Density at 23 °C	g/cm ³	1.05	1.1

PROCESSING

Mix ratio	Parts by weight
RenCast® 6427 A	100
RenCast® 5427 B	20

Mix the two components thoroughly in the ratio indicated.
Evacuated material will improve properties. Post-curing will improve final properties.

PROPERTIES

Resin/Hardener mix:	Volume	Unit	RenCast® 6427 A RenCast® 5427 B
Appearance			Clear, yellowish
Mix viscosity 25°C		mPa s	1200 - 1300
Pot life at 25°C	1000 ml	min	35 - 40
Max. layer thickness		mm	70 - 80
Demoulding time* at 23°C		hours	16 - 20

Density	ISO 1183	g/cm ³	1.1
Hardness	ISO 868	Shore A	70 - 75
Tear propagation resistance	DIN 53356	kN/m	5 - 6
Tensile strength	ISO 527-2	MPas	5 - 6
Elongation at break	ISO 527-2	%	200 - 250

* To avoid creep, always store parts on a flat surface without stressing.
Follow recommendation for curing before subjecting the parts to loading.

STORAGE

The resin and hardeners described in this instruction sheet have the shelf lives shown provided they are stored at 6 - 40°C in a dry place and sealed containers, preferably those in which they are supplied.

**WORKING
CONDITIONS**

The product should be used when in the temperature range 18-25°C

PACKAGING

System	RenCast® 6427 A	RenCast® 5427 B
Quantity and Weight	20 Kg	4 Kg
Quantity and Weight		

**HANDLING
PRECAUTIONS****Caution**

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

RenCast is a registered trademark of Huntsman Corporation or an affiliate thereof.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Office :
Huntsman Advanced Materials (Switzerland) GmbH
Klybeckstrasse 200
CH-4057 BASEL
Switzerland
+41 61 299 1111